

Wälzlagerstähle

100Cr6	1.3505
100CrMo7.3	1.3536
100CrMnMo8	1.3539

Einsatzstähle

16MnCr5	1.7131
20NiCrMo 2-2	1.6523
C15	1.0401
32CrB4	1.7076

Baustähle

TSTE 355 (LF2/F52)	1.0566
S235J2G3	1.0116
S460N	1.9801
S690 QL	1.8988

Vergütungsstähle

18CrNiMo7-6	1.6587
C60	1.0601
42CrMo4	1.7225
42CrMoS4	1.7227
34CrNiMo6	1.6582
30CrNiMo8	1.6580

Werkzeugstähle

X38CrMoV5.1.1.	1.2342
X40CrMoV5.1	1.2344
95MnWCr5	1.2510
55NiCrMoV7	1.2713
28NiCrMoV10	1.2740
46NiCrMoV16-6	1.2746
HS6-5-2-5	1.3243
HS6-5-3	1.3344

Verschleißfeste Stähle

X120Mn12	1.3401
X110Mn 14	1.3402
46NiCrMoV16-6	1.2746

Hochwarmfeste Stähle

X10CrMoVNb9-1 (P91)	1.4903
10CrMo9-10(F22)	1.7380
12Ni14 (LF 3)	1.5637

Nitrierstähle

31CrMoV9	1.8519
31CrMo12	1.8515
34CrAlNi7	1.8550
32CrAlMo7-10	1.8505

Edelstähle

X12Cr13 (AISI 410)	1.4006
X29CrS13	1.4029
X46Cr13	1.4034
X39CrMo17-1	1.4122

